

CALDWELL CHEMICAL COATINGS PRODUCT SPECIFICATION SHEET

Product Name:	Rediframe Brown Plus
Caldwell Formula Number:	726-4209
Customer Part Number:	61280050
Recommended Shelf Life:	6 months
Gloss:	30 +/- 5 using 60-degree gloss meter
Hardness:	H-3H using calibrated lead pencil, ASTM-D3363-93a
Adhesion:	Paint to iron phosphated steel, ASTM. -D3359-97, not more than 10 % loss
Recommended DFT:	1.0-1.3 mil no metal showing on part
Cure or Bake:	300 F @ 20 minutes. 100 MEK double rubs, no removal of paint
Humidity:	ASTM.-D1735-93a. 50 hrs. unscribed
Salt Spray:	240 hours unscribed, 5% salt, 95F

The information and data contained herein are believed to be reliable, based upon our knowledge and knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OR MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials, Buyer must make its own determination of the suitability of any product for its use.